

# PATENT ABSTRACTS OF JAPAN

(11)Publication number : 2000-245823

(43)Date of publication of application : 12.09.2000

---

(51)Int.Cl.

A61L 27/00

A61F 2/28

---

(21)Application number : 11-055842

(71)Applicant : MITSUBISHI MATERIALS CORP

(22)Date of filing : 03.03.1999

(72)Inventor : TAKEUCHI HIROYASU  
HIRANO MASAHIRO

---

## (54) COMPOSITE CALCIUM PHOSPHASTE ARTIFICIAL BONE

### (57)Abstract:

**PROBLEM TO BE SOLVED:** To enable to fit well to shape of a bone deficient part, to have biocompatibility and to excellently form bones in the peripheral part of material.

**SOLUTION:** A composite calcium phosphate artificial bone has a block-like calcium phosphate artificial bone at its center, and paste-like calcium phosphate arranged in the periphery. The paste-like calcium phosphate comprises calcium phosphate as a main component of power and water as a main component of liquid. The calcium phosphate is one selected from each simple substance of  $\alpha$ -tricalcium phosphate or tetracalcium phosphate and mixture thereof, a mixture of  $\alpha$ -tricalcium phosphate, tetracalcium phosphate and calcium hydrogenphosphate and/or dicalcium hydrogenphosphate, a mixture of  $\alpha$ -tricalcium phosphate and calcium hydrogenphosphate and/or dicalcium hydrogenphosphate, or a mixture of tetracalcium phosphate and calcium hydrogenphosphate and/or dicalcium hydrogenphosphate.

---

## LEGAL STATUS

[Date of request for examination]

31.03.2000

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

3322231

[Date of registration]

28.06.2002

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]